# Tiffany

*Classic Shapes. Contemporary Colour. Endless Charm.*

Step into a world of subtle colour and timeless style with the Tiffany Series





Step into a world of subtle colour and timeless style with the Tiffany Series – a beautiful range designed to elevate everyday spaces.  Tiffany brings warmth and versatility every room.



Available in a refined palette of White, Sage, Blue, and Butter, this series blends nostalgic charm with modern simplicity.



Designed for creativity – use the solid tones to create checkerboard patterns, horizontal or vertical stripes, or pair with matching Oversized Fishscale tiles in Sage, Blue, and Butter for a playful, textural contrast.


Colours:
**Solid**: White, Sage, Blue, Butter
**Fishscale**: Sage, Blue, Butter

Whether you're after a soft, tonal scheme or a bold visual statement, the Tiffany Series delivers on both style and flexibility – one tile, endless possibilities.


# Tiffany

GNS CERAMICS
EXCLUSIVELY WHOLESALE


White




Butter



Sage



Blue



200x200mm

Matt

Floor Cat. 4

V2
Variation

Glazed
Porcelain

16

Made in China

P3

GNS Ceramics recommends that our retail shops pass on the following information to the installer and end-user.

Click or Scan for Installation Instructions


Ceramic tiles are only one component of a much larger building system. It is our experience that failure of any tiling system is very often the result of a combination of factors. For example; inappropriate design, type of substrate, surface preparation, temperature during installation, adhesives, incompatibility of products, product failure, environmental factors skill and knowledge of the installers etc; the latter being supplied or controlled by a variety of manufacturers and tradesmen. GNS Ceramics has no involvement in the design, selling and installation processes and once goods have been dispatched from our warehouse we have no control over where and how these products are used. As a result the project manager, and or the tiler are the only people in a position to ensure that all the components used in a project are compatible and that the product is installed in accordance with the Australian Building Code and the Australian Standards.

Installation Instructions for all types of tiles can be found in the GNS Ceramics Price List, and on our website. We suggest these are followed at all times.

**Cleaning and Maintenance**

Do not use abrasive cleaners and chemicals which could permanently scratch and damage the surface of the tile. For daily cleaning we recommend the use of a mild PH Neutral detergent. Should a more vigorous cleaning programme be required we recommend the use of a proprietary tile cleaner from a specialty tile supplier.

**Colour & Pattern Variation Guide**




Uniform Appearance | Slight Variation | Moderate Variation | High Variation

**Slip Resistance**

The best way to minimise the risk of slipping is through safe design principals. This involves a risk management approach which evaluates the likelihood and consequence of an incident to occur. Slip resistive flooring is only one of the design components to consider, other design features should also be considered, including awnings, airlocks, matting and a suitable cleaning regime to reduce the extent of contaminates. Visual aids, warning signs, handrails and lighting, along with the footwear to be worn, should also be considered.

All ceramic tiles can be slippery, particularly when wet. This includes tiles, commonly used in wet areas such as bathrooms. It is important that customers be aware of the potential danger of wet ceramic tiles and seek advice from the retailer as to the level of slip-resistance of any particular tile, and its suitability for the intended application. If there is any doubt, tiles should be tested for slip-resistance immediately after being laid, under the conditions that they will be subject to during use. While tiles may achieve an acceptable standard in a laboratory test, it is quite probable that the performance in-situ will be less than expected, due to installation methods, wear & tear, cleaning regimes and unforeseen circumstances. Test results should therefore to be seen as a relative guide to estimate the merits of one tile versus another and should be used in conjunction with the Australian Building Code and the relevant Australian Standards. Further information on slip resistance is provided in the Australian Standards HB198:2014 - An Introductory guide to the slip resistance of pedestrian surface materials.

There are many factors beyond the control of the supplier that can affect the level of slip-resistance of tiles, or contribute to the incidents of injury through slipping. Consequently, the laboratory test results presented here must not be viewed to mean that GNS Ceramics Pty Ltd, is providing any warranty, nor will accept any liability for personal injury or accidents arising from the selection or installation of tiles under any circumstances.

**Classes of Use**

The classification has taken into account the recommendations of the Australian Standards; however, they are given for general guidance only. They are valid for the given application under **NORMAL CONDITIONS** and should not be taken to provide accurate product specifications for specific requirements.

**WARNING: Other standards and building code requirements may affect your selection of tiles.**

Consideration should be given to the footwear, type of pedestrian traffic and cleaning methods expected. Floors should be adequately protected against soiling from following trades during installation; they should also be protected against scratching dirt at the entrances to building by interposing footwear cleaning devices. For example, mats, shoe scrapers, static devices, etc.

**CLASS 4** - Floor coverings that are walked on by regular traffic with some scratching dirt so that conditions are more severe than CLASS 3; For example, entrances, laundries with external access, living areas, entertainment areas, patio's, sales rooms, motels.

中国认可
国际互认
检测
TESTING
CNAS L1978

190000122473

# TEST REPORT

REPORT NO. 25201904596

NAME OF SAMPLES CERAMIC TILES

APPLICANT SHENYANG HAOSONG CERAMIC CO. LTD

MANUFACTURER SHENYANG HAOSONG CERAMIC CO. LTD

DATE OF INSPECTION 22/10/2019 – 21/11/2019(DD/MM/YY)

STATE KEY TESTING LABORATORY OF BUILDING CERAMICS AND SANITARY WARE
INSPECTION AND QUARANTINE COMPREHENSIVE TECHNOLOGY CENTRE OF
FOSHAN ENTRY-EXIT INSPECTION & QUARANTINE BUREAU



Tiffany 23/01/2026 扫描全能王 创建 Page 5 of 20

# INSPECTION AND QUARANTINE COMPREHENSIVE TECHNOLOGY CENTRE OF FOSHAN ENTRY-EXIT INSPECTION & QUARANTINE BUREAU

# TEST REPORT

**Report No: 25201904596** 

| | | | |
|---|---|---|---|
| **Name of Sample** | **CERAMIC TILES** | **Nominal Size** | **20cm×20cm** |
| **Type** | **GLAZED** | **Work size** | **199mm×199mm×8.3mm** |
| **Group** | **B I b** | **Quantity of Samples** | **30 Pieces** |
| **Mark of Samples** | **M4** | **Description of Samples** | **The samples are sound, intact and fit for test.** |
| **Manufacturer** | **SHENYANG HAOSONG CERAMIC CO. LTD** | **Address of Manufacturer** | **—** |
| **Telephone of Manufacturer** | **—** | **Fax of Manufacturer** | **—** |
| **Samples selected by** | **Name: MUHAMAD MUZHAFAR FIKRI BIN ISMAIL<br>Institution: SIRIM QAS INTERNATIONAL SDN. BHD.<br>Date: 10/10/2019** | **Received on** | **21/10/2019** |
| **Test Standard** | **MS ISO 13006:2014 *Ceramic tiles – Definitions, classification, characteristics and marking*** | | |
| **Conclusion of Test** | **The results conform to the requirement of standard MS ISO 13006:2014 with respect to the test items.** | | |
| **Stamp of Inspection Unit** | **Date: 25/11/2019** | **Address of Test Unit** | **Address: 2/F, Building 18, Lanshi International Metal Exchange Center, Kuiqiyi Road, Chancheng District, Foshan, Guangdong, China (528000)<br>Tel: 86-757-83960558<br>86-757-83827991<br>Fax: 86-757-83827971<br>E-mail: fsiqtc@163.com<br>Url: http://www.fsiqtc.com/** |
| **Notes** | **1. All inspections are carried out conscientiously to the best of our knowledge and ability. This report does not in any respect absolve the other related parties from his contractual and legal obligations.<br>2. This report shall not be reproduced, except in full, without the prior written approval from the issuing laboratory.<br>3. The results in this report apply to the samples only.** | | |


**Tested by** 杨明彦 **Inspected by** 陈世发 **Approved by** 肖勇.12



Tiffany 23/01/2026 扫描全能王 创建 Page 6 of 20

# TEST REPORT



| | |
|---|---|
| **Description of Samples** | **The samples are sound, intact and fit for test.** |
| **Photo of Samples** | <br> |

# TEST REPORT

**Report No: 25201904596** 

MS ISO 13006:2014 *Ceramic tiles – Definitions, classification, characteristics and marking*

| Clause | Properties | Test Method | Requirements | | Results | Verdicts |
|---|---|---|---|---|---|---|
| Annex H Table H.1 | **Dimensions and surface quality** | | | | | |
| | **Length and width** The deviation, of the average size for each tile from the work size | MS ISO 10545-2:2002 | N≥15cm | ±0.6% | -0.04%~+0.21% | P |
| | | | | ±2.0mm | -0.1mm~+0.4mm | P |
| | **Thickness** The deviation of the average thickness of each tile from the work size thickness | MS ISO 10545-2:2002 | N≥15cm | ±5% | +1.5%~+3.7% | P |
| | | | | ±0.5mm | +0.1mm ~+0.3mm | P |
| | **Straightness of sides** The maximum deviation from straightness related to the corresponding work sizes | MS ISO 10545-2:2002 | N≥15cm | ±0.5% | +0.02%~+0.07% | P |
| | | | | ±1.5mm | 0 ~+0.1mm | P |
| | **Rectangularity** The maximum deviation from Rectangularity related to the corresponding work sizes | MS ISO 10545-2:2002 | N≥15cm | ±0.5% | +0.20%~+0.28% | P |
| | | | | ±2.0mm | +0.4mm~+0.6mm | P |
| | **Surface flatness**: The maximum deviation from flatness | | | | | |
| | a) centre curvature, related to diagonal calculated from the work size; | MS ISO 10545-2:2002 | N≥15cm | ±0.5% | -0.17%~-0.12% | P |
| | | | | ±2.0mm | -0.5mm~-0.3mm | P |
| | b) edge curvature, related to the corresponding work sizes; | MS ISO 10545-2:2002 | N≥15cm | ±0.5% | +0.07%~+0.12% | P |
| | | | | ±2.0mm | +0.1mm~+0.2mm | P |
| | c) warpage, related to diagonal calculated from the work size. | MS ISO 10545-2:2002 | N≥15cm | ±0.5% | +0.10%~+0.16% | P |
| | | | | ±2.0mm | +0.3mm~+0.4mm | P |
| | **Surface quality** | MS ISO 10545-2:2002 | A minimum of 95% of the tiles shall be free from visible defects inspected vertically at 1.0m. | | 100% | P |
| | **Physical properties** | | | | | |
| | **Water absorption** Percent mass fraction | MS ISO 10545-3:2001 | 0.5% < $E_b$≤3% | | 2.4% | P |
| | | | Individual maximum 3.3% | | 1.3%~2.9% | P |



Tiffany 23/01/2026 扫描全能王 创建 

# TEST REPORT



MS ISO 13006:2014 *Ceramic tiles – Definitions, classification, characteristics and marking*

| Clause | Properties | Test Method | Requirements | Results | Verdicts |
|---|---|---|---|---|---|
| Annex H Table H.1 | **Breaking strength, in N** | MS ISO 10545-4:2003 | ⩾1100 | 1753 | P |
| | **Modulus of rupture, in N/mm²** Not applicable to tiles with breaking strength ≥ 3000N | MS ISO 10545-4:2003 | Minimum 30 | 44.6 | P |
| | | | Individual minimum 27 | 41.5~46.9 | P |
| | **Abrasion resistance** Resistance to surface abrasion of glazed tiles intended for use on floors | MS ISO 10545-7:2001 | Report abrasion class | Class 4 | — |
| | | | Report cycles passed | 2100 | — |
| | **Crazing resistance**: glazed tiles | MS ISO 10545-11:2001 | Required | Fully resistance | P |
| | **Chemical properties** | | | | |
| | **Resistance to chemicals** | | | | |
| | Resistance to household chemicals and swimming pool salts | | | | |
| | a) Household chemicals: Ammonium chloride, 100g/L | MS ISO 10545-13:2018 | Minimum GB | A | P |
| | b) Swimming pool salts: Sodium hypochlorite solution, 20mg/L | MS ISO 10545-13:2018 | Minimum GB | A | P |
| | Resistance to low concentrations of acids and alkalis | | | | |
| | a) Hydrochloric acid solution, 3% (v/v) | MS ISO 10545-13:2018 | Manufacturer to state classification | LA | — |
| | b) Citric acid solution, 100g/L | MS ISO 10545-13:2018 | Manufacturer to state classification | LA | — |
| | c) Potassium hydroxide, 30g/L | MS ISO 10545-13:2018 | Manufacturer to state classification | LA | — |
| | Resistance to high concentrations of acids and alkalis | | | | |
| | a) Hydrochloric acid solution, 18% (v/v) | MS ISO 10545-13:2018 | Test method available | HA | — |
| | b) Lactic acid, 5 % (v/v) | MS ISO 10545-13:2018 | Test method available | HA | — |
| | c) Potassium hydroxide, 100g/L | MS ISO 10545-13:2018 | Test method available | HA | — |
| | **Resistance to staining** | | | | |
| | a) Green staining agent in light oil | MS ISO 10545-14:2018 | Minimum Class 3 | Class 5 | P |
| | b) Red staining agent in light oil | MS ISO 10545-14:2018 | Minimum Class 3 | Class 5 | P |
| | c) Iodine, 13g/L solution in alcohol | MS ISO 10545-14:2018 | Minimum Class 3 | Class 5 | P |
| | d) Olive oil | MS ISO 10545-14:2018 | Minimum Class 3 | Class 5 | P |

Possible test case verdicts
1. P(ass) : *Test item does meet the requirement.*
2. F(ail) : *Test item does not meet the requirement.*
3. —: *Verdict was not carried out.*
4. N/A : *Test case does not apply to the test item.*

*** ***

End of Test Report



Tiffany 23/01/2026 扫描全能王 创建

# TEST REPORT

**No. : XMIN2506001335CM02_EN**

**Date : 2025-06-23**



CUSTOMER NAME: CAPUCINO CERAMICS

ADDRESS: F22nd-23rd, South Tower, Citic Poly Plaza, TianHong Rd, LeCong Town, ShunDe District, Foshan City, Guangdong Province, P.R. China 528000

Sample Name : Ceramic Tiles

Product Specification : 200*200*8.2

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

**********

Date of Receipt : 2025-06-16

Testing Period : 2025-06-16 ~ 2025-06-23

Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services Co.,Ltd. Xiamen Branch.

Bryan Hong
Authorized signatory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China 361101 t (86-592) 5765857 www.sgsgroup.com.cn
中国·福建·厦门·火炬（翔安）产业区翔虹路31号 邮编: 361101 t (86-592) 5765857 sgs.china@sgs.com

Member of the SGS Group (SGS SA)

# TEST REPORT

**No. : XMIN2506001335CM02_EN**


**Date : 2025-06-23**



Summary of Results:

| No. | Test Item | Test Method | Result |
|---|---|---|---|
| 1 | Wet Pendulum Test | AS 4586-2013 Amdt 1-2017 Appendix A | SRV "wet": 36<br>Class: P3 |

Original Sample Photo:




Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China 361101 t (86-592) 5765857 www.sgsgroup.com.cn
中国·福建·厦门·火炬（翔安）产业区翔虹路31号 邮编：361101 t (86-592) 5765857 sgs.china@sgs.com

# TEST REPORT

**No. : XMIN2506001335CM02_EN**

**Date : 2025-06-23**



Test Item: Wet Pendulum Test

Sample Description: See photo

Test Method: AS 4586-2013 Amdt 1-2017 Appendix A

Test Condition:

Specimen: 200mm×200mm, 6pcs

Type of slider: slider 96 (4S rubber)

Test surface: see photo

Test direction: see photo

Test Result:

| Specimen No. | 1 | 2 | 3 | 4 | 5 | 6 |
|---|---|---|---|---|---|---|
| Mean of British Pendulum Number (for each test surface) | 36 | 40 | 38 | 36 | 36 | 39 |
| Slip resistance value (SRV "wet") | 38 | | | | | |
| Class | P3 | | | | | |

Classification of pedestrian surface materials according to the wet pendulum test:

| Class | Pendulum SRV (slider 96) |
|---|---|
| P5 | >54 |
| P4 | 45-54 |
| P3 | 35-44 |
| P2 | 25-34 |
| P1 | 12-24 |
| P0 | <12 |

********End of report*********

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/en/Terms-and-Conditions. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.
Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

No.31 Xianghong Road, Xiang'An Torch Industrial Zone, Xiamen, Fujian Province, China 361101 t (86-592) 5765857 www.sgsgroup.com.cn
中国·福建·厦门·火炬（翔安）产业区翔虹路31号 邮编: 361101 t (86-592) 5765857 sgs.china@sgs.com

# MATERIAL SAFETY DATA SHEET

## 1. PRODUCT IDENTIFICATION

| | |
|---|---|
| Common name: | Ceramic Tile (For purposes of this SDS, the term “ceramic” encompasses alltypes of tile products.) |
| Manufacturer Name: | Max Glory International Ltd |
| Address: | 22nd~23rd Floor, South Tower, Citic Poly Plaza, TianHong Rd, LeCong Town, ShunDe District, Foshan City, Guangdong Province, P. R. China 528000<br>Tel: +86-757-8307 1852 or 8313 4180 - 8010<br>Fax: +86-757-8313 4181 |
| Emergency Assistance: | Tel: +86-757-8307 1852 or 8313 4180 - 8010 |
| Recommended Use: | Building Material – for floor and wall cladding |

## 2. HAZARDS IDENTIFICATION

Tile products are odorless, stable, non-flammable, does not release any hazardous chemical and are considered as non-hazardous to health under normal conditions of use. However, dust containing crystalline silica is produced by the cutting and grinding of tiles during installation or by operations such as demolition / removal projects. Respiratory, hand and eye protection may be needed to prevent excess exposure to airborne particulates from these activities. The hazards identified below apply to tile usage under these conditions.

| | |
|---|---|
| Signal Word: | Danger |
| Hazardous substance: | Crystalline Silica |


Category 3 (Respiratory tract irritation) (H335)


Category 1A(Carcinogenicity) (H372)

Issued Date: 3rd September 2024

| | |
|---|---|
| Hazard Statements: | May cause CANCER (inhalation) (H350)<br>May cause respiratory irritation (H335)<br>Causes damage to organs (lung/respiratory) through prolonged or repeated exposure (inhalation) (H372) |
| Precautionary Statements: | Do not handle until all safety precautions have been read and understood. (P202)<br>Do not breathe dust/spray. (P260+P261)<br>Wash skin thoroughly after handling. (P264)<br>Do not eat, drink or smoke when using this product. (P270)<br>Wear protective gloves, protective clothing, eye protection, faceprotection. (P280) |
| Potential Health Effects: | Inhalation: Do not breathe dust. See “Health Hazards” in Section 11 for more details. |

## 3. COMPOSITION / INFORMATION ON INGREDIENTS

**Chemical characterization**: Mixtures
**Description**: Mixture of substances listed below with non-hazardous additions

**Dangerous components**: Not applicable
**Non-hazardous components**:
Tiles consist of a mixture of predominantly clay types and other naturally occurring mineral substances. After mixing with water and pressing of the tile the bisque is fired at very high temperature. During the firing process very stable crystal grid structures are formed in which the individual chemical elements are incorporated.

Main constituents of ceramic tiles (bisque) are silicon oxide (65 – 75%) and aluminium oxide (15- 25%).

Main constituents of the glazing layer are silicon oxide (approx. 50%), aluminium oxide (approx. 10%) and calcium oxide (approx. 10%); furthermore, the glazing layer contains small percentages of the following substances: sodium oxide, manganese oxide, iron oxide, magnesium oxide, potassium oxide and barium oxide.

## 4. FIRST AID MEASURES

Applicable during cutting or changing the shape of the tile during installation and removal whenpotential hazards associated with dusts which may be produced.

Eyes: Immediately flush eyes with large amounts of water for at least 15 minutes if dust getsin eyes. Get medical attention if irritation persists.

Skin: Wash thoroughly after working with tiles.

Inhalation: Remove to fresh air if exposed to large amounts of tile dust. Administer artificial respiration if breathing has stopped. Keep victim at rest. Call for prompt medical attention.

Ingestion: Not applicable for intact tiles.

Have emergency eyewash station available in area where tiles are cut.

## 5. FIRE-FIGHTING MEASURES AND INFORMATION

| | |
|---|---|
| Flash Point (Method Used): | Not applicable |
| Auto ignition Temperature: | Not applicable |
| Flammable Limits (% by Volume in Air): | LEL - not applicable<br>UEL - not applicable |
| Fire Extinguishing Media: | None required Non-flammable |
| Special Fire Fighting Procedures: | None |
| requiredFire and Explosion Hazards: | None |

## 6. ACCIDENTAL RELEASE MEASURES

Avoid creating excessive dust. Clean up dust with a vacuum system with a High-efficiency particulate (HEPA) air filter vacuum or damp sweeping. See Section 8 of this SDS concerning PPE information for clean-up.

## 7. HANDLING AND STORAGE

Handling: No specific chemical hazards when handling whole product. When cutting, grinding orhacking see Section 8 on Exposure Control.

Storage: Dry covered condition recommended. Do not store near acids. If tiles contact some acids,damage/discoloration to the surface may occur. Shelf life is unlimited.

## 8. EXPOSURE CONTROLS / PERSONAL PROTECTION

Occupational exposure limits

OSHA PEL : 0.10 mg/m³ as respirable crystalline silica
ACGIH TLV : 0.05 mg/m³ as respirable crystalline silica

Control of occupational exposure:

Technical measures: Bring tiles to size using a score-and-cut tile cutter instead of sawing or grinding methods. During sawing or grinding of tiles or removal of old tiles, always use local exhaust ventilation combined with collection of dust, in the case of sawing or grinding, wet cutting methods are more preferable in which the sawing or grinding equipment is equipped with water supply or with application of (semi) automatic removal equipment with moistening facility.

Ventilation: Use adequate ventilation to keep exposure to dust below recommended exposure levels.Avoid inhalation of dust. The highest probability of silica exposure occurs during installation using drycutting methods or during removal of installed tile.

Respiratory Protection: Use of a properly fitted and approved particulate respirator is recommended when cutting tiles for installation or during the removal of installed tile.

Eye Protection: Use dust-proof goggles or safety glasses with side shields. Contact lenses may absorb irritants. Do not wear contact lenses in work areas.

Skin Protection: Cotton or leather work gloves should be worn when cutting this product to minimize skin exposure to dust and/or cuts. Wash hands prior to eating, drinking, or smoking, and at the end ofthe work shift, after cutting operations are conducted.

NOTE: Personal protection information in Section 8 is based on general information for normal uses and conditions. Where special or unusual uses or conditions exist, it is suggested that the assistance of an industrial hygienist or other qualified professional be obtained.

## 9. PHYSICAL AND CHEMICAL PROPERTIES

| | |
|---|---|
| Appearance: | Brittle solid; colour may vary |
| Odor: | Odorless |
| Melting Point: | Not Available (>2200 0F) |
| Boiling Point: | Not applicable |
| Vapor Pressure: | Not applicable |
| Vapor Density (Air = 1): | Not applicable |
| Solubility in Water: | Insoluble |
| Specific Gravity (H2) = 1): | 1.6 to 2.1 |
| Percent Volatile by Volume: | Not applicable |
| Evaporation Rate (Ethyl Ether = 1): | Not applicable |
| Viscosity: | Not applicable |
| Volatility: | 0 g/L Volatile Organic Compounds (VOCs) |

## 10. STABILITY AND REACTIVITY

| | |
|---|---|
| Stability: | Stable in current form. |
| Conditions to Avoid: | Avoid contact with acids (e.g., acetic, hydrofluoric, etc.) |
| Incompatible Materials to Avoid: | Avoid contact with acids (e.g., acetic, hydrofluoric, etc.) |
| Hazardous Polymerization: | Will not occur. |
| Hazardous Decomposition Products: | None. |

## 11. TOXICOLOGICAL INFORMATION

**Acute Effects**

No acute effects from exposure to intact tile are known. Working with broken or cut tile produces a potential for cuts to the hands and exposed body parts. Acute effects such as eye irritation may occur if associated with high dust operations such as dry cutting tile or during the removal of installed tile. In very rare cases, symptoms of acute silicosis, a form of silicosis may develop following acute exposureto extremely dusty environments. Signs such as labored breathing and early fatigue may indicate silicosis; however, these same symptoms can arise from many other causes.

**Chronic Effects**

No chronic effects are known for exposure to intact tile. Long-term, continual exposure to respirable crystalline silica at or above established permissible occupational exposure limits may lead to the development of silicosis, a nodular pulmonary fibrosis (NPF). NPFs are also associated with pulmonary tuberculosis, bronchitis, emphysema, and other airway diseases. This type of chronic exposure to silica dust may also result in the development of autoimmune disorders, chronic renal disease, and other adverse health effects.

Recent epidemiologic studies demonstrate that workers exposed to elevated silica concentrations have a significant risk of developing chronic silicosis. Signs such as labored breathing and early fatigue may indicate silicosis; however, these same symptoms can also arise from many other causes.

**Potential Adverse Interactions**

Silicosis may be complicated by severe mycobacterial or fungal infections and result in tuberculosis (TB). Epidemiologic studies have established that silicosis is a risk factor for developing TB. Any existing respiratory or pulmonary diseases may be complicated by exposure to respirable crystalline silica. Smoking may increase the risk of adverse effects if done in conjunction with occupational exposure to silica dust at or above permissible exposure limits.

**Carcinogen Status**

Respirable crystalline silica is classified by the International Agency for Research on Cancer (IRAC) as a Group I Carcinogen (carcinogenic to humans).

**Overview of Animal Testing**

Short term experimental studies of rats have found that intratracheal instillation of quartz particles leads to the formation of discrete silicotic nodules in rats, mice and hamsters.

**Oral (silica) Lethality**

LD50 Rat oral >22,500 mg/kg
LD50 Mouse oral >15,000 mg/kg
LC50 Carp >10,000 mg/l (per 72 hr.)

## 12. ECOLOGICAL INFORMATION

There are no known hazardous decomposition products.
Persistence and degradability : Not biodegradable
Aquatic toxicity : Not known

## 13. DISPOSAL CONSIDERATIONS

Under normal conditions these products are not considered hazardous waste and do not release hazardous materials after installation. Dispose in accordance with Federal, state and local waste disposal regulations

## 14. TRANSPORTATION INFORMATION

| | |
|---|---|
| D.O.T Shipping Name: | Not applicable |
| Hazard Class: | Non-regulated (For disposal purposes material is non-hazardous Class III regulated material) |
| ID Number: | Not applicable |
| Marking: | Not applicable |
| Label: | None |
| Placard: | None |
| Hazardous Substance/RQ: | Not applicable |
| Shipping Description: | Porcelain/Ceramic |
| TilesPackaging References: | None |

## 15. REGULATORY INFORMATION

Refer to the regulatory exposure limits for dust released during cutting, grinding or removal. (See Item 8).

Note: The information in this data sheet provides information related to the potential hazards associated with dusts which may be produced during cutting or otherwise changing the shape of the tile during installation and/or removal.

## 16. ADDITIONAL INFORMATION

Global Harmonization Identification System
GHIS: Health: 3 Fire: 4 Reactivity: 4

Hazardous Material Identification System
HMIS: Health: 1 Fire: 0 Reactivity: 0

Issued Date: 3rd September 2024

The information given is to the best of Max Glory International Ltd's knowledge and is believed to be correct as of the date indicated. However, no representation, warranty or guarantee is made to its accuracy, reliability or completeness. This shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship. It is the user's responsibility to satisfy itself as to the suitability and completeness of such information for their own particular use.

Please take note of the following additional safety measures when installing or processing tiles:

- Wear adequate working clothes
- Wear knee protection
- Wear safety shoes
- Use appropriate lifting and transporting equipment

Issued Date: 3rd September 2024